

## PRODUCT DATA SHEET

# Sika BlackSeal® Elastic

### BRANZ APPRAISED LIQUID APPLIED FLEXIBLE BITUMEN DAMP-PROOF MEMBRANE



#### DESCRIPTION

Sika BlackSeal® Elastic is a BRANZ appraised polymer modified water based bitumen emulsion.

#### USES

Sika BlackSeal® Elastic has been formulated for use as a waterproof membrane behind retaining walls and as a damp-proof membrane for underground structures. Sika BlackSeal® Elastic can be applied to concrete, concrete block and brick-work, wood and metal.

#### CHARACTERISTICS / ADVANTAGES

- BRANZ Appraised certificate No.770 [2018]
- Meets Clause B2 Durability, not less than 50 years, E2 External Moisture and F2 Hazardous Building Materials
- Appraised as an Alternative Solution in terms of the New Zealand Building Code
- Improved moisture vapour flow resistance of >300 MNs/g.
- Fast cure, recoat in 4 hours
- Complies with AS/NZS 4020, tested for use in contact with drinking water (potable water)\*
- Can be mixed with sand and cement to create waterproof screeds and mortars
- Water based, free from solvents
- Simple to apply by brush or roller
- Excellent adhesion to concrete and masonry
- Very low water permeability
- Can be applied to green concrete
- Resistant to ground salts

#### APPROVALS / STANDARDS

- BRANZ Appraised certificate No.770 [2018]
- Appraised as an Alternative Solution in terms of the New Zealand Building Code
- Complies with AS/NZS 4020, tested for use in contact with drinking water (potable water)\*
- Exceeds the NZS 3604:2011 moisture vapour permeability requirements for a damp-proof membrane. Sika BlackSeal® Elastic has been appraised by BRANZ as a damp-proof membrane behind concrete masonry basement walls, and insitu or precast concrete where the membrane is protected against damage, where drainage has been placed, and installation has been completed by a Licensed Building Practitioner trained and approved by Sika (NZ) Limited. Go to [learnhow.sika.co.nz](http://learnhow.sika.co.nz) to obtain your application certificate. Refer to BRANZ Appraisal No. 770 (2018).

#### PRODUCT INFORMATION

<b>Packaging</b>	4 litre and 20 litre containers
<b>Shelf Life</b>	Shelf life is twelve (12) months when stored as stated under "Storage".

<b>Storage Conditions</b>	Store in original containers in a dry place below 35°C and away from frost.
<b>Colour</b>	Blue/Grey when wet. Black when dry.
<b>Density</b>	1.03 kg/litre
<b>Solid content by weight</b>	60%
<b>Elongation at Break</b>	>1950%
<b>Tensile Adhesion Strength</b>	250 kN/m <sup>2</sup>
<b>Permeability to Water Vapour</b>	340 MNs/g

## APPLICATION INFORMATION

<b>Consumption</b>	Minimum application rate is 1 litre per m <sup>2</sup> (in addition to the primer coat). Ideally this should be applied as two full undiluted coats at a coverage rate of approximately 2m <sup>2</sup> / litre / coat, depending on the nature of the surface being treated.
<b>Waiting Time / Overcoating</b>	Recoat time = minimum 4 hours, or longer in cold temperatures.
<b>Drying Time</b>	Touch dry in 1 to 2 hours. Recoat time = minimum 4 hours, or longer in cold temperatures.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LIMITATIONS

- Do not expose to sunlight.
- Do not overcoat with paints as staining will occur, and if exposed to sunlight the paint film will crack.
- Sika BlackSeal® Elastic is recommended for use only as described in the "Uses" section of this data sheet.
- \*Sika BlackSeal® Elastic is not recommended for use internally on water retaining structures.
- Visit our website to watch the "How to apply Sika BlackSeal Elastic" video. (If you're a NZ LBP, do the short quiz and get your exclusive Sika BlackSeal Elastic certificate.) [Sika® BlackSeal® Elastic](#)

## ECOLOGY HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

Visit our website to watch the "How to apply Sika BlackSeal Elastic" video. (If you're a NZ LBP, do the short quiz and get your exclusive Sika BlackSeal Elastic certificate.) [Sika® BlackSeal® Elastic](#)

### SUBSTRATE QUALITY

Clean down surface to be treated removing all dust, grease, laitance and foreign matter. Remove any form release agent residues and curing compounds by high pressure waterblasting, grit blasting or mechanical wire brushing. Grind back smooth any dags, sharp edges or ridges. Any surface irregularities should be filled using Sika MonoTop repair mortars or Sikadur-41 epoxy repair mortar. Form a cove where required in internal corners. Stir Sika BlackSeal® Elastic thoroughly before use.

### SUBSTRATE PREPARATION

#### CONTROL JOINTS:

Movement control joints in concrete or concrete masonry should be sealed with Sika BlackSeal®-1 prior to applying Sika BlackSeal® Elastic. However, for joints under pressure, Sikaflex® Tank N should be used. Please note that Sikaflex® Tank N will require an isolation tape such as a pure aluminium foil tape overlay to prevent plasticiser migration from the Sika BlackSeal® Elastic. Refer to the Sika BlackSeal®-1 or Sikaflex® Tank N datasheets for details on joint sizes and application methods. For high movement joints refer to the Sika technical department.

**PRIMING:** A primer coat of 1 part clean water to 1 part Sika BlackSeal® Elastic should be used. Add water slowly and mix thoroughly. Apply at a rate of approximately 4m<sup>2</sup>/litre.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

### Sika (NZ) Limited

85-91 Patiki Road  
Avondale, Auckland 1026  
New Zealand  
0800 745 269  
www.sika.co.nz



### Product Data Sheet

Sika BlackSeal® Elastic  
May 2022, Version 04.02  
020706301000000109

SikaBlackSealElastic-en-NZ-(05-2022)-4-2.pdf

